



D2741 BLADE



D2741F FLAT PATTERN



SECTION A-A

RELEASED
2013-08-13

NOTES:

- 1) MATERIAL: AISI 4130N STEEL BAR PER MIL-S-6758 OR AMS 6345/6348/6370/6528
REF DART SPEC. M4130N-B0.500X3.000
- 2) FINISH: POWDER COAT "WHITE" (4.3.5.2) PER DART QSI 005 4.3
- 3) TOLERANCES: PER DART QSI 018 UNLESS OTHERWISE NOTED
- 4) UNITS: INCHES UNLESS OTHERWISE NOTED
- 5) BREAK SHARP EDGES: 0.030 TO 0.060 MAX
- 6) IDENTIFICATION: WITH DART P/N "D2741" AND B/N "BXXXXX" PER DART QSI 044 6.1 (FINE POINT PAINT MARKER)
- 7) WEIGHT: 3.3 lbs
- 8) SYMMETRY: ABOUT \bar{C}
- 9) HEAT TREAT TO MIN. ULTIMATE TENSILE STRENGTH = 152 ksi AND MIN. YIELD TENSILE STRENGTH = 141 ksi
PER MIL-S-6758 OR AMS2759/1E AFTER MACHINING.
ACCEPTABLE TO VERIFY TENSILE STRENGTH BY HARDNESS TEST PER ASTM E18 TO 34-40 HRC.
- 10) OPTIONAL: ONLY REQUIRED WHEN MAKING D350-636-215/-216/-217/-218

D	ADD Ø0.201 HOLES AND NOTE 10 (ZN D7-1). REMOVE -041/-043 OPTIONS REFORMAT DWG. REF PAR11-72	SFM	13.02.21
C	LARGER HOLE, ADD RADIUS AND CHAMFER ADD -041/-043 OPTIONS	PH	06.01.12
B	CHANGE C'SINK TO C'BORE	CP	98.09.01
A	NEW ISSUE	DS	98.04.16
REV.	DESCRIPTION	BY	DATE
DESIGN	DS	DART AEROSPACE USA, INC. KENT, WA	
DRAWN	SFM		
CHECKED		DRAWING NO.	REV. D
MFG. APPR.		D2741	SHEET 1 OF 1
APPROVED		TITLE	SCALE
DE APPR.		BLADE	NTS
DATE	13.02.21	<small>COPYRIGHT © 1998 BY DART AEROSPACE USA, INC. THIS DOCUMENT IS PRIVATE AND CONFIDENTIAL AND IS SUPPLIED ON THE EXPRESS CONDITION THAT IT IS NOT TO BE USED FOR ANY PURPOSE OR COPIED OR COMMUNICATED TO ANY OTHER PERSON WITHOUT WRITTEN PERMISSION FROM DART AEROSPACE USA, INC.</small>	